




PREMIUM - E



Product Information

Usage classification ^(*)	EN ISO 10874 / EN 685		22
Wear layer	EN ISO 24340 / EN 4291		0.20 mm
Total thickness	EN ISO 24346 / EN 428		2.00 mm
Total weight	EN ISO 23997 / EN 430		1250 g/m ²
Standard widths	EN ISO 24341 / EN 426		2 - 3 - 4 m
Standard length	EN ISO 24341 / EN 426		30 m

Technical Information

Light stability	EN ISO 105 B02		≥ 6
Dimensional Stability	EN ISO 23999 / EN 434		≤ 0.40 %
Underfloor heating	EN 12667		Suitable
Residual Indentation	EN ISO 24343-2 / EN 433		≤ 0.35 mm
Reaction to fire	EN 13501-1		Bfl/S1
Slip resistance	DIN 51130		R10
Dynamic coefficient of friction	EN 13893		> 0.6
Impact sound	EN ISO 717/2		Δ Lw 10 dB

(*) Without print layer